

3312E

Polypropylene Random Copolymer / PPR-Pipe Extrusion

PRODUCT DESCRIPTION

3312E is a PP Random copolymer Natural color special designed for Pipe Extrusion application. Performing the high toughness, balance impact properties, high heat and chemical resistance properties for Hot and Cold water pipe application.

INDUSTRY

- Hot and Cold water system
- Water pressure pipe
- Plumbing and Drinking Water Pipe
- Sewage and Drainage Pipe
- Fitting Injection
- Floor heating system
- Hospital used

PRODUCT FEATURE

- Suitable for Hot water up to 95°C
- Great processibility and Stability
- Long Service Life

REGULATION COMPLIANCE

- Other regulations : Please contact our staff

PHYSICAL PROPERTIES	TEST METHOD	UNIT	VALUE*
Melt Flow Rate (2.16 kg / 2.16°C)	ASTM D 1238	g/10 min	0.25
Density	ASTM D 792	g/cm ³	0.90
MECHANICAL PROPERTIES			
Tensile Strength at Yield	ASTM D 638	MPa	27
Flexural Modulus	ASTM D 790	MPa	850
Izod Notched Impact Strength 23°C	ASTM D 256	J/m	600
THERMAL PROPERTY			
Heat Distortion Temperature	ASTM D 648	°C	75

*The properties can vary significantly depending on the incoming source and supply capability.

Remark: The values presented on the above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.

3312E

Polypropylene Random Copolymer / PPR-Pipe Extrusion

PROCESSING TECHNIQUE

Extruder Temperature	180 - 225 °C
Adapter Temperature	240 - 250 °C
Die Temperature	250 - 260 °C

*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

PRODUCT PACKAGING

- 25 kg loose bag
- 750 kg Jumbo bag

For further information, contact the IRPC's sales representative.

STORAGE

The resin should be stored in a dry location with good housekeeping practices during storage, transferring and handling. Process enclosures and adequate ventilation should be used to avoid excessive dust accumulation. Resin should be protected from direct sunlight, temperatures above 38°C (100°F) and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time. The container should be kept closed to prevent contamination. For the additional recommended storage conditions, please refer to SDS.

SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.

DISCLAIMER

The data indicated above are the results of our investigations, knowledge and correspond to the state of the art as of the date of publication and the data refer to the state of the laws at the date of issue and this information expires after a break in delivery lasting more than 12 months or in case of regulatory changes. This statement is not intended and should not be construed as specification, warranty or representation of any sort for which IRPC would be legal responsibility. The applicability or the accuracy of this statement or the suitability of our products cannot be guaranteed because the conditions of use on the part of our users are beyond our control. IRPC gives no guarantees or makes no warranties which extend beyond the description above herein. Nothing herein shall constitute any implied guaranty or warranty of merchantability or fitness for a particular purpose. In the case that IRPC's products are used in combination with other materials, no liability can be accepted. When not utilized in combination with any third-party products, the information included above refers only to our products. Please ask IRPC for a new information if needed. All terms and conditions regarding the supply of IRPC's products shall be subject to IRPC's Policy, in the case of a dispute, the Company's decision is final and is not subject to any appeal.