

HD7200B

High Density Polyethylene Resin

Special Characteristics : InnoPlus HD7200B is extra high molecular weight high density polyethylene blow molding grade which is recommended for 20-120 litre drums. It has excellent processability and exhibits very high impact strength, stiffness and extremely environment stress crack resistance.

Typical Applications : Hazardous chemical drums, Agricultural chemical drums.

Typical Properties :

| Properties | HD7200B | Unit | Test Method |
|---|----------|--------------------|-------------|
| Physical Properties | | | |
| Melt Flow Rate (190 °C, 2.16 kg) | 0.05 | g/10 min | ASTM D1238 |
| Melt Flow Rate (190 °C, 21.6 kg) | 8.5 | g/10 min | ASTM D1238 |
| Density | 0.956 | g/cm ³ | ASTM D1505 |
| Vicat softening point | 124 | °C | ASTM D1525 |
| Melting Temperature | 134 | °C | ASTM D3418 |
| Mechanical Properties (Based on compression specimens) | | | |
| Tensile Strength at Yield | 300 | kg/cm ² | ASTM D638 |
| Tensile Strength at Break | 350 | kg/cm ² | ASTM D638 |
| Elongation at Break | 800 | % | ASTM D638 |
| Stiffness | 10,000 | kg/cm ² | ASTM D747 |
| Flexural Modulus | 12,000 | kg/cm ² | ASTM D790 |
| Notched Izod Impact Strength | 25 (NB)* | kg.cm/cm | ASTM D256 |
| Durometer Hardness | 63 | Shore D | ASTM D2240 |
| ESCR, F ₅₀ (Condition B, 25 % Igepal) | >1000 | hrs | ASTM D1693 |

* NB = Non Break

Recommendation :

Extruder temperature : 195 - 220 °C

Die temperature : 200 - 220 °C

FDA Statement :

Food and Drug Administration US FDA 21 CFR 177.1520 and Commission Regulation (EU) 10/2011. More compliance regulations and standards that related to the product shall be exhibited in Product Regulatory Certificate (PRC) document.

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.