

LD1840D

Low Density Polyethylene Resin

Special Characteristics : InnoPlus LD1840D is produced by high pressure tubular process, a technology licensed by LyondellBasell. This grade provides high melt strength leading to excellent bubble stability during blown-film process. Film from InnoPlus LD1840D offers high tear strength, good impact strength, good tensile strength and elongation.

Typical Applications : InnoPlus LD1840D is recommended for producing the agricultural films and general purpose film.

Additives : No Slip and No Antiblock

Typical Properties :

Properties	LD1840D	Unit	Test Method
Physical Properties (Based on pellets and press-molded sheet)			
Melt Flow Rate (190 °C, 2.16 kg)	0.22	g/10 min	ISO 1133
Density	0.920	g/cm ³	ISO 1183
Melting Temperature	111	°C	ISO 11357
Vicat softening point	93	°C	ASTM D1525

Film Properties* (Based on blown film)

Max. Tensile Strength (MD/TD)	25 / 25	MPa	ISO 527
Ultimate Elongation (MD/TD)	500 / 750	%	ISO 527
Dart Drop Impact	250	g	ASTM D1709
Tear Resistance (MD/TD)	280 / 350	gf	ASTM D1922
Haze	8	%	ASTM D1003
Gloss (20°)	37	-	ASTM D2457

* film properties obtained from 70 microns film which was blown film extruded at blow up ratio 2.0

Recommendation:

The recommended temperature setting is in the range of 170 - 220 °C

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.