

# PC20006JGY

Polycarbonate/ABS Compound

**Special Characteristics :** PC20006JGY is a product of injection grade of grey coloring PC/ABS compound which is specially designed for good heat and high impact resistance. It also exhibits high ductility and tensile strength as well as suitable for outdoor applications.

**Typical Applications :** Injection molded part for outdoor uses

**Typical Properties :**

Properties	PC20006JGY	Unit	Test Method
<b>Physical Properties</b>			
Melt Flow Rate (260°C, 5 kg)	16	g/10 min	ISO 1133
Density	1.13	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical Properties</b>			
Tensile Strength at Yield	52	MPa	ISO 527
Elongation at Break	50	%	ISO 527
Tensile Modulus	2,300	MPa	ISO 527
Flexural Strength	75	MPa	ISO 178
Flexural Modulus	2,300	MPa	ISO 178
Notched Charpy Impact Strength at 23°C	45	kJ/m <sup>2</sup>	ISO 179
Notched Charpy Impact Strength at -30°C	25	kJ/m <sup>2</sup>	ISO 179
<b>Thermal Properties</b>			
Heat Deflection Temperature at 0.45 MPa	119	°C	ISO 75
Heat Deflection Temperature at 1.80 MPa	102	°C	ISO 75
Vicat Softening Point at 50 N	120	°C	ISO 306

**Recommendation :**

For Injection Molding

- Drying conditions: 80°C at least 4 hrs before using
- Melt temperature: 210–250°C
- Mold temperature: 55–70°C
- Screw speed for screw diameter of 35 mm: 30–60 rpm
- Back pressure 10–15 MPa

**Disclaimer:** To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

*Note :* Properties reported here are typical values of the product, not to be considered as specifications.

GC makes no representations as to the accuracy or completeness of the information contained herein.