

S908C

Polystyrene Compound

Special Characteristics: S908C is a conductive HIPS compound based on high impact polystyrene with impact modified suitable for injection, extrusion sheet and thermoforming. It is intended for a wide range of applications, particularly in the thermoforming for the electronics, electrical, disk-drive as shipping or component trays.

Typical Applications: Black conductive HIPS specimens

Typical Properties:

Properties	S908C	Unit	Test Method
Physical Properties			
Melt Flow Rate (200°C, 5 kg)	2.2	g/10 min	ASTM D1238
Density	1.11	g/cm ³	ASTM D792
Mechanical Properties			
Tensile Strength at Yield	31	MPa	ASTM D638
Elongation at Break	28	%	ASTM D638
Tensile Modulus	1,940	MPa	ASTM D638
Flexural Strength	54	MPa	ASTM D790
Flexural Modulus	2,480	MPa	ASTM D790
Notched Izod Impact Strength	168	J/m	ASTM D256
Thermal Properties			
Vicat Softening Point	89	°C	ASTM D1525
Heat Deflection Temperature	79	°C	ASTM D648
Electrical Properties			
Surface Resistivity (at 23°C, 50% RH)	10 ³ -10 ⁵	Ohm/square	ASTM D257

Recommendation:

Storage condition: S908C, owing to its moisture sensitive, is recommended to be properly wrapped and stored in dry and well-ventilated area.

Processing:

- Pre-drying in a dehumidifying dryer is recommended e.g., 3–4 hours at 70–80°C before sheet extrusion.
- Recommend processing temperature of conductive HIPS compound is 180–270°C*.

* The modification of processing condition shall be performed under the recommendation.

Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however, we do not assume any liability what so ever for the accuracy and completeness of such information. We make no warranties which extend beyond the description contained herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose. It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of our products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.
GC makes no representations as to the accuracy or completeness of the information contained herein.