

1140H

Polypropylene Homopolymer /
Super High Clarity Extrusion Sheet for Thermoforming Applications

PRODUCT DESCRIPTION

1140H is a Polypropylene Homopolymer with the characteristic of good stiffness and balane impact. It is suitable for various applications like blow molding and sheet extrusion.

TYPICAL APPLICATION

- Super high clarity thermoforming packaging
- Super high clarity extrusion sheet
- Extrusion Blow Molding bottle (EBM)

PRODUCT FEATURES

- Good stiffness with Impact balance
- High deep down thermoforming
- Super high clarity

COMPLIANCE

- FDA US 21 CFR 177.1520
- Commission Regulation (EU) No. 10/2011
- RoHS
- REACH

PHYSICAL PROPERTIES	TEST METHOD	UNIT	VALUE
Melt Flow Index (2.16 kg/230 °C)	ASTM D1238	g/10 min	2.0
Density	ASTM D792	g/cm ³	0.90
Tensile Strength at Yield	ASTM D638	MPa	39
Elongation at Yield	ASTM D638	%	10
Izod Notched Impact Strength (at 23 °C)	ASTM D256	J/m	45
Flexural Modulus (1% SECANT)	ASTM D790	MPa	1850
Rockwell Hardness	ASTM D785	R-Scale	110
Heat Distortion Temperature (0.45 MPa)	ASTM D648	°C	120
Haze (1 mm)	ASTM D1003	%	25

Remark: The values presented on the above are typical laboratory, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitable of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.

1140H

Polypropylene Homopolymer /
Super High Clarity Extrusion Sheet for Thermoforming Applications

PROCESSING TECHNIQUE

Cylinder Temperature	: 180 - 210 °C
Die Temperature	: 190 - 210 °C
Cooling Water Temperature	: 20 - 25 °C
Air Pressure	: 6 - 7 Bar

*However, the actual processing conditions depend on mold design, power of machine, equipment and other environments.

PRODUCT PACKAGING

- 25 kg loose bag
- 25 kg stretch wrap on palletized
- 750 kg jumbo bag
- Bulk truck

STORAGE

Storage in 20 - 80% relative humidity at ambient temperature preferably not higher than 38 °C (100 °F).

Dry environment with the exclusion of contamination.

Protection against direct sunlight, radiation and artificial light containing UV-Radiation.

Protection from ozone-generating electrical devices.

Under these optimal conditions, the physical properties of resins should remain stable with the exception of the yellowness index which is expected to increase over time.

More information provide in safety data sheet.

SAFETY

This product is not classified as hazardous material for more information please refer to safety data sheet.

RECYCLING

It is an undisputed fact that the product can be recycled or disposed of without any problem.